

**MINING / CONSTRUCTION**

**TEKCRETE PRO**

**MICROSILICA ENHANCED DRY PROCESS SHOTCRETE (GUNIT) MATERIAL**

**DESCRIPTION**


TekCrete Pro is supplied as a ready-to-use dry powder, formulated for dry mix shotcrete requiring only the addition of water. TekCrete Pro is a specially formulated blend of micro silica cement, PVA high modulus fibers and carefully graded aggregates which when mixed with water results in a high build, dense, low absorption shotcrete. The required low water-to-cement ratio ensures high early and ultimate strengths. TekCrete Pro shrinkage compensation minimizes stress at the bond line. Each 60 lb bag of TekCrete Pro creates approximately 0.45 cubic feet of material.

**USES**

TekCrete Pro is ideal for large vertical and overhead structural repairs where a reliable dry process shotcrete or gunit is required. Bridge and parking structures, supporting columns and beams, seawalls, tunnel linings, dams, mine entry support, and mine sealing are just a few of the applications for TekCrete Pro.

**ADVANTAGES**

- Fiber reinforced – High modulus PVA fibers to help reduce cracking potential
- Reliability – Factory quality-controlled materials ensuring consistent proportioning, mixing and packaging
- Relatively fine aggregate – Carefully graded to allow easier finishing and thinner layers



**APPLICATION METHOD**

**Preparation**

If spraying on rock, clean surfaces of loose or friable materials, mud or foreign matter that might weaken shotcrete bonding with high-pressure water, as moisture will allow for a better bond between the product and the base material.

Spraying of shotcrete (gunit) mortar is a skilled process and requires trained and experienced operators to achieve best results. The operator controlling the nozzle will determine the quality of the finish as he proceeds with the application. It is therefore essential that only experienced applicators who are familiar with the process and are fully aware of the requirements and details of the application techniques be employed.

Remove or protect objects that are not to be covered with TekCrete Pro.

*Continued>*

**Placement**

The placement of TekCrete Pro depends primarily on the ability of the dry process shotcrete nozzleman who should be certified in the placement of shotcrete. Ensure air and substrate temperatures are greater than 40° F (4.5° C) during and for 48 hours after application of shotcrete. Follow the instructions for the specific shotcrete equipment you are using.

The best time to spray is directly after surface preparation when the base material is first exposed. After coating the area with TekCrete Pro and allowing the product to set firmly, keep the work area moist using a fine mist water spray for one day in order to generate best results.

**Curing**

Curing is essential to optimize the physical properties of TekCrete Pro and minimize plastic shrinkage. TekCrete Pro should be cured immediately after the material has reached initial set in accordance with ACI 308R-16 (Guide to External Curing of Concrete). Curing is particularly important where rapid moisture loss can take place such as low humidity, high winds and high temperatures.

Purge all TekCrete Pro material from the pump and lines upon project completion. Follow the pump manufacturer’s instructions for additional specific clean-up procedures.

**TECHNICAL DATA**

The data below is laboratory data only. It may vary in practice due to thermal exchange between cement and substrate, temperature and other factors.

Parameter	Time / Value
<b>Compressive Strength ASTM C39</b>	24 hrs / 6000 psi (41.3 MPa) 7 days / 7000 psi (48.2 MPa) 28 days / 7500 psi (51.7 MPa)
<b>Dry Shrinkage ASTM C341</b>	56 days / -0.030 (%)
<b>Wet Expansion ASTM C341</b>	56 days / 0.002 (%)
<b>Modulus of Elasticity ASTM C469</b>	28 days / 5517 (ksi)
<b>Freeze/Thaw Resistance ASTM C666</b>	216 C / RDM @ 98 (%)
<b>Rapid Chloride Permeability ASTM C1202</b>	28 days classified “very low”
<b>Tensile Bond Strength ASTM C1583</b>	28 days 420 psi (2.8 MPa)

## SAFETY INSTRUCTIONS AND LIMITATIONS

Good housekeeping is needed during storage, transfer, handling and use of this material to avoid excessive dust accumulation. Never add material to this product unless instructed by Minova USA, Inc.

## PACKAGING AND TRANSPORTATION

TekCrete Pro is available in 60 lb bags, 48 bags per pallet and 3,000 and 1,500 lb supersacks.

## STORAGE AND SHELF LIFE

Twelve months, in cool dry conditions.

## DISPOSAL

If this product as supplied becomes a waste, it does not meet the criteria of a hazardous waste as defined under the Resource Conservation and Recovery Act (RCRA) 40 CFR 261. Dispose of material in accordance with all applicable federal, state/provincial and local laws and regulations. Regulations may vary in different locations. Waste characterizations and compliance with applicable laws are the responsibility solely of the waste generator.

## APPROVALS AND CERTIFICATES



an ISO 9001:2015  
Quality Management System Certified Company.

## DISCLAIMER

The Minova Logo is a registered trademark of Minova International, Ltd.

Copyright © 2019 Minova. All rights reserved.

All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non-infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

## ADDITIONAL DOCUMENTATION

Started more than 135 years ago, Minova is a global manufacturer and supplier of chemical and mechanical earth control products and support equipment. With manufacturing plants on five continents and operations in more than 25 countries, Minova is an industry-leading provider of ground support solutions for the underground mining, construction and energy industries.

If further information is required consult Minova Americas website: [www.minovaglobal.com](http://www.minovaglobal.com).

- TekCrete Pro Safety Data Sheet (SDS)
- Minova TekCrete Pro Product Specification

## MANUFACTURER

Trading name of Minova USA, Inc.  
150 Summer Court  
Georgetown, KY 40324  
USA

## CUSTOMER SERVICE

[Customer.salesupport@minovaglobal.com](mailto:Customer.salesupport@minovaglobal.com)  
Phone: +1 (800) 626-2948  
Alt Phone: +1 (502) 863-6800  
Fax: +1 (502) 863-6805