

MINING / CONSTRUCTION

Minotor C

DRY-SPRAY CONCRETE

DESCRIPTION

Minotor C is a dry-spray concrete based on high-quality Portland cement with the addition of other mineral components, which when mixed at the site of application with the appropriate amount of water set to become a durable concrete material.

APPLICATION AND USE

- Dry-spray concrete
- Sealing and reinforcing of sidewalls, floor and roof of mining excavations, reservoirs and tunnels
- Construction of sealing and support packs in mines

ADVANTAGES

- Rapid strength gain
- High ultimate strength
- Tight for water and gas
- Resistance to aggressive environments
- Low cost
- Ease and safety of use
- Non-combustibility



TECHNICAL DATA

The data below are laboratory data. They may vary in practice due to surface properties of the substrate, humidity, pressure, and other factors.

PRODUCT CHARACTERISTICS

Parameter	Minotor C
Concrete class EN 12504-1:2011	C35/45
Modulus of elasticity ISO 1920-10:2010	34.6 GPa
Depth of water penetration EN 12390-8:2011	20 mm
Flexural strength EN 196-1:2006	10 MPa

COMPONENT CHARACTERISTICS

Parameter	Minotor C
Colour / form	grey powder with aggregates 2 mm
Amount of water per 25 kg bag	2.5 litres
Pot life at 20 °C	60 minutes
Output	0.50 m ³ /t
Ambient temperature and substrate during application	min.+5 °C; max +35 °C

APPLICATION METHOD

1. Surface preparation

Before application of Minotor C, remove loose fragments of rock, concrete, dust, greasy stains, formwork release agent etc. Make sure that the equipment and main lines located at the work place are secured & protected. In order to improve adhesion to the substrate surface it is recommended to dump it with water prior to application. For the best results, wet the concrete surface 24 hours before performing the repair. Seal active water with plugging grout Minostop. In case of major water leaks from the ground, eliminate them by injecting organic resins (eg Ekopur HW, Krzemopur S). As the auxiliary method in case of large leaks, a water intake with drainage pipe may be used.

2. Equipment

For the application of Minotor C, use equipment designed for shotcreting using the dry spraying method.

3. Execution

Adjusted water/powder ratio should be ~ 0.10 for dry spray method. Recommended distance from the substrate is about 1 - 2 m. The nozzle should be continuously moved along the sprayed area to get a tight layer having the proper, continuous thickness. The air velocity should be adjusted to level where material bonds to substrate but not too much to destroy structure and cause too high rebound. The more exact coverage may be achieved applying 2 layers.

4. Cleaning

Clean tools with water. When hardened clean mechanically.

5. Curing

Minotor C requires curing, particularly under strong drying conditions. Minotor C should be cured immediately after finishing in accordance with good concrete practice. In very fast drying conditions, supplementary curing with polythene sheeting taped down at the edges should be used.

In cold conditions, the finished repair must be protected from freezing.

SAFETY INSTRUCTIONS AND LIMITATIONS

It is recommended that gloves, eye protection and a dust mask are used when handle Minotor C. For more details refer to our Material Safety Data Sheet.

The material should not be applied when the substrate and/or air temperature is 5°C and falling. At 5°C static temperature or at 5°C and rising, the application may proceed.

At ambient temperatures above 35°C, the material should be stored in the shade and cool water used for mixing.

PACKAGING AND TRANSPORTATION

25 kg valve sack, 40 bags per pallet. Other packing on request.

STORAGE AND SHELF LIFE

Shelf life 6 months when stored in dry and cool conditions.

DISPOSAL

Follow local regulations.

APPROVALS AND CERTIFICATES

1. Mining Certificate OBAC/0484/CB/17
2. Hygienic Certificate HK/B/0772/01/2018

DISCLAIMER

The Minova Logo is a registered trademark.

Copyright © 2019 Minova. All rights reserved

All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non-

infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

ME-NS/TE/03/44-01/ Minotor C e01 (April 2009)

ADDITIONAL DOCUMENTATION

- Minotor C MSDS

LIST OF REPRESENTATIVES

- AUSTRIA: Minova MAI GmbH
- CZECH REPUBLIC: Minova Bohemia s.r.o.
- FRANCE / BELGIUM: Sales office Minova France / Belgium
- GERMANY: Minova CarboTech GmbH
- ITALY: Minova CarboTech GmbH Italy branch
- KAZAKHSTAN: Minova Kazakhstan LLP
- POLAND: Minova Ekochem S.A.; Minova Arnall Sp. z o.o.; Minova Ksante Sp. z o.o.
- RUSSIA: ZAO "Carbo-ZAKK"
- SLOVAKIA: Minova Bohemia s. r. o., organizačná zložka
- SOUTH AFRICA: Minova Africa (Pty) Ltd.
- SPAIN: Minova Codiv S.L.U.
- SWEDEN / NORWAY: Minova Nordic AB
- UNITED KINGDOM: Minova Weldgrip Ltd.; Minova International Ltd.
- APAC: Minova Australia Pty Ltd.
- AMERICAS: Minova USA Inc.

CUSTOMER SERVICE

For additional support options available at your area, contact our local offices.

www.minovaglobal.com